

AK Steel 17-7 PH® Precipitation Hardening Stainless Steel, Condition C

Category : Metal , Ferrous Metal , Martensitic , Stainless Steel , Precipitation Hardening Stainless

Material Notes:

AK Steel 17-7 PH® provides high strength and hardness, excellent fatigue properties, good corrosion resistance, good formability, and minimum distortion upon heat treatment. This alloy provides valuable property combinations particularly well suited for aerospace applications. This special alloy also provides benefits for other applications requiring high strength and good corrosion resistance, as well as excellent properties for flat springs at temperatures up to 600°F (310°C). The material supplied from the mill is in Condition A. After fabrication, and conditioning treatments, the material is precipitation hardened into either Condition TH 1050 or Condition RH 950. To achieve the highest mechanical properties Condition A material is transformed to martensite at the mill by cold reduction to Condition C. After fabrication by the user a single low-temperature heat treatment is preformed to achieve condition CH 900. Information provided by AK Steel

Order this product through the following link:

http://www.lookpolymers.com/polymer_AK-Steel-17-7-PH-Precipitation-Hardening-Stainless-Steel-Condition-C.php

Physical Properties	Metric	English	Comments
Density	7.70 g/cc	0.278 lb/in ³	Typical

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	43	43	
Tensile Strength, Ultimate	1517 MPa	220000 psi	
Tensile Strength, Yield	1310 MPa @Strain 0.200 %	190000 psi @Strain 0.200 %	
Elongation at Break	5.0 %	5.0 %	in 2 inches
Modulus of Elasticity	200 GPa	29000 ksi	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	0.75 - 1.5 %	0.75 - 1.5 %	
Carbon, C	<= 0.090 %	<= 0.090 %	
Chromium, Cr	16 - 18 %	16 - 18 %	
Iron, Fe	70.59 - 76.75 %	70.59 - 76.75 %	As Remainder
Manganese, Mn	<= 1.0 %	<= 1.0 %	
Nickel, Ni	6.5 - 7.75 %	6.5 - 7.75 %	
Phosphorous, P	<= 0.040 %	<= 0.040 %	

<small>Silicon, Si</small> Component Elements Properties	<small><= 1.0 %</small> Metric	<small><= 1.0 %</small> English	Comments
Sulfur, S	<= 0.030 %	<= 0.030 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China