## API Megol AM DP2217/60PBT SEBS Adhesion Modified Overmolding for Polyesters

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

## Material Notes:

Over-molding allows for the creation of composite finished products in a single phase, removing the need for successive gluing or mechanical fixing steps. This also reduces environmental impact as there are no VOC emissions from adhesives and, as the components are not made from a range of incompatible materials, they are more easily recycled at the end of their useful life. The over-molding process can be used in highly technical applications such as components for the automotive industry, shells and casings for power tools, parts for domestic appliances, and seals which can be molded directly onto the frame.Information provided by A.P.I. SpA

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_API-Megol-AM-DP221760PBT-SEBS-Adhesion-Modified-Overmolding-for-Polyesters.php

Physical Properties	Metric	English	Comments	
Density	0.970 g/cc	0.0350 lb/in³	ASTM D 792	
Mechanical Properties	Metric	English	Comments	
Hardness, Shore A	60	60	ASTM D 2240	
	@Time 15.0 sec	@Time 0.00417 hour		
Tensile Strength	4.50 MPa	653 psi	ASTM D 638	
Elongation at Break	600 %	600 %	ASTM D 638	
100% Modulus	0.00200 GPa	0.290 ksi	ASTM D 638	
300% Modulus	0.00350 GPa	0.508 ksi	ASTM D 638	
Tear Strength	30.0 kN/m	171 pli	ASTM D 624	
Compression Set	35 %	35 %		
	@Temperature 23.0 °C, Time 259000 sec	@Temperature 73.4 °F, Time 72.0 hour	ASTM D 395	
	70 %	70 %	ASTM D 395	
	@Temperature 70.0 °C, Time 86400 sec	@Temperature 158 °F, Time 24.0 hour		
	85 %	85 %		
	@Temperature 100 °C, Time 86400 sec	@Temperature 212 °F, Time 24.0 hour	ASTM D 395	

Descriptive Properties	Value	Comments
Compatibility	РВТ	



Descriptive Properties	Value	Comments
	PET	
Food contact	On Request	
Hygroscopicity	Slightly	
Main Features	Easy Processability	
Ozone Aging Resistance	Excellent	72h, 40°C, 200 ppcm, Tension = 20%
Processing	Injection Molding	
Weathering	Good	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China