

ATG s.r.l. EPDM Ethylene-Propylene Terpolymer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATG-srl-EPDM-Ethylene-Propylene-Terpolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.860 g/cc	0.860 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 85	40 - 85	
Tensile Strength, Ultimate	6.00 - 18.0 MPa	870 - 2610 psi	
Elongation at Break	150 - 500 %	150 - 500 %	
Rebound	35 - 55 %	35 - 55 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	155 °C	311 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Descriptive Properties	Value	Comments
Abrasion Resistance	medium	
Chemical Resistance to Animal and Vegetable Oils and Greases	medium	
Chemical Resistance to Aromatic Hydrocarbons	none	
Chemical Resistance to Chloride Solvents	none	
Chemical Resistance to Distilled Water	high	
Chemical Resistance to Ketones	high	
Chemical Resistance to Maximum Concentrated Alkalis (at 50°C)	high	
Chemical Resistance to Medium-High Concentrated Acids (at 50°C)	medium	
Chemical Resistance to Mineral Oils and Aliphatic Hydrocarbons	none	
Compression set at 100°C	high	
Impermeability at gas (Oxygen and Nitrogen)	low	

Resistance to Flame Descriptive Properties	None Value	Comments
Resistance to Heat Aging	medium	
Resistance to Low Temperatures	low	
Resistance to Ozone and Weathering	high	
Tear Strength	medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China