

ATG s.r.l. XNBR Carboxylated Nitrile Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATG-srl-XNBR-Carboxylated-Nitrile-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50 - 95	50 - 95	
Tensile Strength, Ultimate	8.00 - 23.0 MPa	1160 - 3340 psi	
Elongation at Break	200 - 725 %	200 - 725 %	
Rebound	10 - 45 %	10 - 45 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	
Minimum Service Temperature, Air	-45.0 °C	-49.0 °F	

Descriptive Properties	Value	Comments
Abrasion Resistance	high	
Chemical Resistance to Animal and Vegetable Oils and Greases	high	
Chemical Resistance to Aromatic Hydrocarbons	low	
Chemical Resistance to Chloride Solvents	none	
Chemical Resistance to Distilled Water	high	
Chemical Resistance to Ketones	none	
Chemical Resistance to Maximum Concentrated Alkalis (at 50°C)	medium	
Chemical Resistance to Medium-High Concentrated Acids (at 50°C)	none	
Chemical Resistance to Mineral Oils and Aliphatic Hydrocarbons	medium	
Compression set at 100°C	medium	
Impermeability at gas (Oxygen and Nitrogen)	medium	

Resistance to Flame Descriptive Properties	Value	Comments
Resistance to Heat Aging	medium	
Resistance to Low Temperatures	medium	
Resistance to Ozone and Weathering	medium	
Tear Strength	medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China