

ATI Allegheny Ludlum 310Si Austenitic Stainless Steel

Category : Metal , Ferrous Metal , Stainless Steel , T 300 Series Stainless Steel

Material Notes:

Characteristics: comparable corrosion resistance, superior resistance to oxidation, and the retention of a larger fraction of room temperature strength than common austenitic alloys. Good creep deformation resistance. Applications: Heat treatment industry-conveyor belts, rollers, burner parts, refractory supports, retorts linings, oven linings, fans, tube hangers, baskets, and trays. Chemical process industry- containers for hot concentrated acids, ammonia, and sulfur dioxide. Food processing industry- used in contact with hot acetic and citric acid. Information provided by Allegheny Ludlum

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATI-Allegheny-Ludlum-310Si-Austenitic-Stainless-Steel.php

Physical Properties	Metric	English	Comments
Density	8.03 g/cc	0.290 lb/in ³	

Mechanical Properties	Metric	English	Comments
Creep Strength	20.0 MPa	2900 psi	1% creep
	@Temperature 788 °C, Time 3.60e+7 sec	@Temperature 1450 °F, Time 10000 hour	
Rupture Strength	138 MPa	20000 psi	1% creep
	@Temperature 593 °C, Time 3.60e+7 sec	@Temperature 1100 °F, Time 10000 hour	
Modulus of Elasticity	200 GPa	29000 ksi	
Poissons Ratio	0.30	0.30	calculated
Shear Modulus	77.0 GPa	11200 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	15.9 µm/m-°C	8.83 µin/in-°F	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
	17.1 µm/m-°C	9.50 µin/in-°F	

Thermal Properties	Metric @Temperature 20.0 - 300 °C	English @Temperature 68.0 - 530 °F	Comments
	18.9 $\mu\text{m}/\text{m}\cdot\text{°C}$	10.5 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 1000 °C	@Temperature 68.0 - 1830 °F	
Specific Heat Capacity	0.502 J/g-°C	0.120 BTU/lb-°F	
	@Temperature 0.000 - 100 °C	@Temperature 32.0 - 212 °F	
Thermal Conductivity	13.8 W/m-K	95.8 BTU-in/hr-ft ² -°F	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
	18.7 W/m-K	130 BTU-in/hr-ft ² -°F	
	@Temperature 20.0 - 500 °C	@Temperature 68.0 - 932 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.20 %	0.20 %	
Chromium, Cr	24 - 26 %	24 - 26 %	
Iron, Fe	47.13 - 53.13 %	47.13 - 53.13 %	As Remainder
Manganese, Mn	2.0 %	2.0 %	
Nickel, Ni	19 - 22 %	19 - 22 %	
Nitrogen, N	0.11 %	0.11 %	
Phosphorous, P	0.045 %	0.045 %	
Silicon, Si	1.5 - 2.5 %	1.5 - 2.5 %	
Sulfur, S	0.015 %	0.015 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000780 ohm-cm	0.0000780 ohm-cm	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Magnetic Permeability	1.02	1.02	at 200H

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China