

## ATI Allegheny Ludlum Stainless Steel AL-6XN® Alloy (UNS N08367), 50% Cold Work

Category : Metal , Ferrous Metal , Stainless Steel , T 300 Series Stainless Steel

### Material Notes:

The AL-6XN® alloy is a superaustenitic stainless steel which was developed by Allegheny Ludlum Corporation. It exhibits far greater resistance to chloride pitting, crevice corrosion and stress-corrosion cracking than exhibited by the standard 300 series stainless steels, and is less costly than the traditional nickel-base corrosion resistance alloys. The AL-6XN alloy has exhibited good performance in a variety of highly corrosive environments. The AL-6XN alloy is available in a wide range of products from including plate, strip, sheet, bar, billet, tubing pipe and castings. Its various product forms are covered by ASME and ASTM specifications. The use of wrought AL-6XN products in the ASME Boiler and Pressure Vessel is covered by Code Case 1997 (latest revision) for Section VII construction and by Code Case N-438 (latest revision) for Section III construction. This use of AL-6XN castings is covered by Code Case 2106 (latest revision) for Section VIII and Code Case 497 (latest revision) for section III construction. The alloy is approved for both welded and unwelded construction under ANSI/ASME B31.1 Code Case 155. Use of AL-6XN alloy in contact with hydrogen sulfide-containing petroleum and natural gas is covered by NACE MR0175-92. Information provided by Allegheny Ludlum Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ATI-Allegheny-Ludlum-Stainless-Steel-AL-6XN-Alloy-UNS-N08367-50-Cold-Work.php](http://www.lookpolymers.com/polymer_ATI-Allegheny-Ludlum-Stainless-Steel-AL-6XN-Alloy-UNS-N08367-50-Cold-Work.php)

Physical Properties	Metric	English	Comments
Density	8.06 g/cc	0.291 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1280 MPa	186000 psi	
Tensile Strength, Yield	1140 MPa @Strain 0.200 %	165000 psi @Strain 0.200 %	
Elongation at Break	3.0 %	3.0 %	in 2" (50 mm)

Thermal Properties	Metric	English	Comments
CTE, linear	15.3 µm/m-°C	8.50 µin/in-°F	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
	15.5 µm/m-°C	8.61 µin/in-°F	
	@Temperature 20.0 - 200 °C	@Temperature 68.0 - 392 °F	
	15.7 µm/m-°C	8.72 µin/in-°F	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
	16.4 µm/m-°C	9.11 µin/in-°F	

Thermal Properties	Metric	English	Comments
	@ Temperature 20.0 - 600 °C	@ Temperature 68.0 - 1110 °F	
	17.6 µm/m-°C	9.78 µin/in-°F	
	@Temperature 20.0 - 800 °C	@Temperature 68.0 - 1470 °F	
Thermal Conductivity	13.7 W/m-K	95.1 BTU-in/hr-ft <sup>2</sup> -°F	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
Melting Point	1320 - 1400 °C	2410 - 2550 °F	
Solidus	1320 °C	2410 °F	
Liquidus	1400 °C	2550 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.030 %	<= 0.030 %	
Chromium, Cr	20 - 22 %	20 - 22 %	
Copper, Cu	<= 0.75 %	<= 0.75 %	
Iron, Fe	48 %	48 %	as balance
Manganese, Mn	<= 2.0 %	<= 2.0 %	
Molybdenum, Mo	6.0 - 7.0 %	6.0 - 7.0 %	
Nickel, Ni	23.5 - 25.5 %	23.5 - 25.5 %	
Nitrogen, N	0.18 - 0.25 %	0.18 - 0.25 %	
Phosphorous, P	<= 0.040 %	<= 0.040 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Sulfur, S	<= 0.030 %	<= 0.030 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000890 ohm-cm	0.0000890 ohm-cm	
Magnetic Permeability	1.0028	1.0028	at 200 Oersted; before cold work

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China