

ATI Allegheny Ludlum Stainless Steel Type 201, 30% Cold Work (UNS S20100)

Category : Metal , Ferrous Metal , Stainless Steel , T S20000 Series Stainless Steel

Material Notes:

Allegheny Ludlum Type 201 and 201L have the greatest tonnage of the Cr-Ni-Mn steels (200 series). Type 201 provides advantages over the 18-8 grades in certain applications. Lower cost manganese and nitrogen additions are partial substitutes for nickel making them more economical alloys. Because they possess a very desirable combination of economy plus good mechanical properties and corrosion resistance properties, they have been used in a wide variety of consumer and transportation applications. This austenitic structure achieves significant strengthening through cold working of the material to produce the transformation to a stronger martensitic structure. Type 201 is resistant to a wide variety of mild to moderately corrosive media. Typical applications for Types 201 and 201L are cookware bodies/lids, hose clamps, piston rings, transit car structural member, transit car roofing/siding, thermal window spacers, air bag containers, and truck trailer posts and door frames. Information provided by Allegheny Ludlum Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATI-Allegheny-Ludlum-Stainless-Steel-Type-201-30-Cold-Work-UNS-S20100.php

Physical Properties	Metric	English	Comments
Density	7.86 g/cc	0.284 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	39	39	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	39	39	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Strength, Ultimate	1214 MPa	176100 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	1224 MPa	177500 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Strength, Yield	996 MPa	144000 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	1050 MPa	152000 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Elongation at Break	11.5 %	11.5 %	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	14 %	14 %	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	16.6 $\mu\text{m}/\text{m}\cdot\text{°C}$	9.22 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
	18.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	10.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 316 °C	@Temperature 68.0 - 601 °F	
	18.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	10.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 358 °C	@Temperature 68.0 - 676 °F	
	20.3 $\mu\text{m}/\text{m}\cdot\text{°C}$	11.3 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 871 °C	@Temperature 68.0 - 1600 °F	
Specific Heat Capacity	0.502 $\text{J}/\text{g}\cdot\text{°C}$	0.120 $\text{BTU}/\text{lb}\cdot\text{°F}$	
	@Temperature 0.000 - 100 °C	@Temperature 32.0 - 212 °F	
Thermal Conductivity	16.3 $\text{W}/\text{m}\cdot\text{K}$	113 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot\text{°F}$	
	@Temperature 100 °C	@Temperature 212 °F	
	23.0 $\text{W}/\text{m}\cdot\text{K}$	160 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot\text{°F}$	
	@Temperature 500 °C	@Temperature 932 °F	
Melting Point	1400 - 1455 °C	2550 - 2651 °F	
Solidus	1400 °C	2550 °F	
Liquidus	1455 °C	2651 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	$\leq 0.15 \%$	$\leq 0.15 \%$	
Chromium, Cr	16 - 18 %	16 - 18 %	
Iron, Fe	72 %	72 %	as balance
Manganese, Mn	5.5 - 7.5 %	5.5 - 7.5 %	
Nickel, Ni	3.5 - 5.5 %	3.5 - 5.5 %	
Nitrogen, N	$\leq 0.25 \%$	$\leq 0.25 \%$	
Silicon, Si	$\leq 1.0 \%$	$\leq 1.0 \%$	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000670 ohm-cm	0.0000670 ohm-cm	
Magnetic Permeability	3.95	3.95	D.C. Permeability (m at 200 H)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China