

ATI Allvac® 6-2-4-2-Si UNS R54620 modified Titanium Alloy

Category : Metal , Nonferrous Metal , Titanium Alloy

Material Notes:

Uses: High performance valves for internal combustion engines. Aerospace and commercial grades. Property values are for samples in the metallurgical condition: 1800°F anneal. Information provided by Allvac, An Allegheny Teledyne Company.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATI-Allvac-6-2-4-2-Si-UNS-R54620-modified-Titanium-Alloy.php

Physical Properties	Metric	English	Comments
Density	4.54 g/cc	0.164 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	28	28	
Tensile Strength, Ultimate	1035 MPa	150100 psi	
Tensile Strength, Yield	966 MPa @Strain 0.200 %	140000 psi @Strain 0.200 %	
Elongation at Break	15 %	15 %	
Reduction of Area	30 %	30 %	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	6.0 %	6.0 %	
Carbon, C	<= 0.10 %	<= 0.10 %	
Hydrogen, H	<= 0.015 %	<= 0.015 %	
Iron, Fe	0.050 %	0.050 %	
Molybdenum, Mo	2.0 %	2.0 %	
Nitrogen, N	0.040 %	0.040 %	
Oxygen, O	0.20 %	0.20 %	
Silicon, Si	0.12 %	0.12 %	
Tin, Sn	2.0 %	2.0 %	
Titanium, Ti	85 %	85 %	as balance
Zirconium, Zr	4.0 %	4.0 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China