

## Aaron Industries AAROLENE® ARPS HI-100-4 Polystyrene Compounded Resin

Category : Polymer , Thermoplastic , Polystyrene (PS)

**Material Notes:**

AAROLENE® ARPS 100 Series Polystyrene Compounded Resin Color may be specified. Melt Flow Index may be specified.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aaron-Industries-AAROLENE-ARPS-HI-100-4-Polystyrene-Compounded-Resin.php](http://www.lookpolymers.com/polymer_Aaron-Industries-AAROLENE-ARPS-HI-100-4-Polystyrene-Compounded-Resin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	ASTM D955
Melt Flow	3.0 - 12 g/10 min @Load 5.00 kg, Temperature 200 °C	3.0 - 12 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	35.2 MPa	5100 psi	ASTM D638
Flexural Modulus	2.12 GPa	307 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China