

Aaron Industries AAROPRENE® AEPC 5000-2 Engineered Polycarbonate Resin

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Melt flow index may be specified.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-AEPC-5000-2-Engineered-Polycarbonate-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	6.0 g/10 min @Load 2.16 kg, Temperature 230 °C	6.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	61.4 MPa	8900 psi	ASTM D638
Flexural Modulus	2.38 GPa	345 ksi	ASTM D790
Izod Impact, Notched	8.54 J/cm	16.0 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	132 °C	270 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China