

## Aaron Industries AAROPRENE® AEPC 5000-4 Engineered Polycarbonate Resin

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

Melt flow index may be specified.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aaron-Industries-AAROPRENE-AEPC-5000-4-Engineered-Polycarbonate-Resin.php](http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-AEPC-5000-4-Engineered-Polycarbonate-Resin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 230 °C	20 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	60.0 MPa	8700 psi	ASTM D638
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790
Izod Impact, Notched	6.94 J/cm	13.0 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	129 °C	265 °F	ASTM D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China