

Aaron Industries AAROPRENE® ATPR 1000 60A Elastomeric Compound

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

AAROPRENE® ATPR 1000 Series Elastomeric Compound Durometer values may be specified. Color may be specified.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-ATPR-1000-60A-Elastomeric-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.00 - 1.10 g/cc	1.00 - 1.10 g/cc	ASTM D792
Melt Flow	80 g/10 min @Load 2.16 kg, Temperature 190 °C	80 g/10 min @Load 4.76 lb, Temperature 374 °F	"E"; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	57 - 63	57 - 63	ASTM D2240
Tensile Strength	6.07 MPa	880 psi	ASTM D412
Elongation at Break	625 %	625 %	ASTM D412
Tensile Modulus	0.00207 GPa	0.300 ksi	ASTM D412
Tear Strength	31.6 kN/m	180 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	355	355	H-18; ASTM D1044

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China