

## Aaron Industries AAROPRENE® ATPR 1000 80A Elastomeric Compound

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

**Material Notes:**

AAROPRENE® ATPR 1000 Series Elastomeric Compound Durometer values may be specified. Color may be specified.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aaron-Industries-AAROPRENE-ATPR-1000-80A-Elastomeric-Compound.php](http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-ATPR-1000-80A-Elastomeric-Compound.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.00 - 1.10 g/cc	1.00 - 1.10 g/cc	ASTM D792
Melt Flow	70 g/10 min @Load 2.16 kg, Temperature 190 °C	70 g/10 min @Load 4.76 lb, Temperature 374 °F	"E"; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	77 - 83	77 - 83	ASTM D2240
Tensile Strength	7.58 MPa	1100 psi	ASTM D412
Elongation at Break	660 %	660 %	ASTM D412
Tensile Modulus	0.00310 GPa	0.450 ksi	ASTM D412
Tear Strength	41.2 kN/m	235 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	380	380	H-18; ASTM D1044

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China