

## Aaron Industries AAROPRENE® CFPP 2010 Calcium Carbonate Filled Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Calcium Carbonate (CaCO3) Filler

### Material Notes:

AAROPRENE® CFPP 2000 Series Reinforced Compounds Melt flow index may be specified. Color may be specified.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aaron-Industries-AAROPRENE-CFPP-2010-Calcium-Carbonate-Filled-Polypropylene.php](http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-CFPP-2010-Calcium-Carbonate-Filled-Polypropylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	ASTM D792
Filler Content	10 %	10 %	Calcium Carbonate; ASTM D2584
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Melt Flow	8.0 - 12 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 - 12 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	32.1 MPa	4650 psi	ASTM D638
Flexural Modulus	1.86 GPa	270 ksi	ASTM D790
Izod Impact, Notched	0.294 J/cm	0.550 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	93.3 °C	200 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China