

Aaron Industries AAROPRENE® CFPP 2030 Calcium Carbonate Filled Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Calcium Carbonate (CaCO3) Filler

Material Notes:

AAROPRENE® CFPP 2000 Series Reinforced Compounds Melt flow index may be specified. Color may be specified.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-CFPP-2030-Calcium-Carbonate-Filled-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Filler Content	30 %	30 %	Calcium Carbonate; ASTM D2584
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	ASTM D955
Melt Flow	8.0 - 12 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 - 12 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	26.2 MPa	3800 psi	ASTM D638
Flexural Modulus	2.14 GPa	310 ksi	ASTM D790
Izod Impact, Notched	0.438 J/cm	0.820 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	220 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China