

Aaron Industries AAROPRENE® GFABS 4020 Glass Filled Acrylonitrile-Butadiene Styrene

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 20% Glass Fiber Filled

Material Notes:

AAROPRENE® GFABS 4000 Series Reinforced Compounds Melt flow index may be specified. Color may be specified.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-GFABS-4020-Glass-Filled-Acrylonitrile-Butadiene-Styrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Filler Content	20 %	20 %	Glass; ASTM D2584
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955
Melt Flow	5.0 - 10 g/10 min	5.0 - 10 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	75.8 MPa	11000 psi	ASTM D638
Flexural Modulus	5.62 GPa	815 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China