

## Aaron Industries AAROPRENE® TFIPP 2010 High Impact Talc Filled Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

### Material Notes:

AAROPRENE® TFIPP 2000 Series Reinforced Compounds Melt flow index may be specified. Color may be specified.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aaron-Industries-AAROPRENE-TFIPP-2010-High-Impact-Talc-Filled-Polypropylene.php](http://www.lookpolymers.com/polymer_Aaron-Industries-AAROPRENE-TFIPP-2010-High-Impact-Talc-Filled-Polypropylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	ASTM D792
Filler Content	10 %	10 %	Talc; ASTM D2584
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Melt Flow	8.0 - 12 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 - 12 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	30.1 MPa	4370 psi	ASTM D638
Flexural Modulus	1.81 GPa	262 ksi	ASTM D790
Izod Impact, Notched	0.726 J/cm	1.36 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	111 °C	231 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China