

Abatron AboCast 8-20/Abocure 8-20 Epoxy (discontinued **)

Category : Polymer , Thermoset , Epoxy

Material Notes:

2-part, clear, solvent-free dielectric epoxy casting compound. Processing: 100/33.00 ratio (pbw); Gel time, 100 g (3.5 oz.): 26 hours at 20°C (68°F). Applications: solventless casting, adhesive, and coating.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Abatron-AboCast-8-20Abocure-8-20-Epoxy-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	115	115	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	40 - 50	40 - 50	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China