

Abatron AboCast 8-22/Abocure 8-22 Epoxy (discontinued **)

Category: Polymer, Thermoset, Epoxy

Material Notes:

2-part, clear, solvent-free dielectric epoxy casting compound. Processing: 100/55.00 ratio (pbw); Gel time, 100 g (3.5 oz.): 23 hours at 20°C (68°F). Applications: solventless casting, adhesive, and coating.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Abatron-AboCast-8-22Abocure-8-22-Epoxy-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	375	375	
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China