

## Abatron AboCast 8-4/Abocure 8-4 Epoxy (discontinued \*\*)

Category : Polymer , Thermoset , Epoxy

### Material Notes:

2-part solvent-free dielectric epoxy casting compound. Processing: 100/60 ratio (pbw); Gel time, 100 g (3.5 oz.): 240 minutes; cures in 3 weeks at 25°C (77°F). Applications: solventless casting, adhesive, and coating.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-AboCast-8-4Abocure-8-4-Epoxy-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Abatron-AboCast-8-4Abocure-8-4-Epoxy-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Water Absorption	0.26 %	0.26 %	in 24 hours.
Viscosity Measurement	1200	1200	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	81	81	
Tensile Strength, Ultimate	50.33 MPa	7300 psi	
Elongation at Break	4.5 %	4.5 %	
Flexural Strength	93.77 MPa	13600 psi	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	8.00e+10 ohm-cm	8.00e+10 ohm-cm	
	@Temperature 93.3 °C	@Temperature 200 °F	
	5.00e+12 ohm-cm	5.00e+12 ohm-cm	
	@Temperature 65.6 °C	@Temperature 150 °F	
	4.00e+15 ohm-cm	4.00e+15 ohm-cm	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Dielectric Constant	3.36	3.36	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.013	0.013	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Processing Properties	Metric	English	Comments
Processing Temperature	25.0 °C	77.0 °F	Curing time: 3 weeks

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**