

Abatron AboCast 8008-6/AboCure 8008-6 Epoxy (discontinued **)

Category : Polymer , Thermoset , Epoxy

Material Notes:

Data provided by the manufacturer, Abatron, Inc. Colorless, "Liquid glass". Very low viscosity. Good color retention and lowest shrinkage.

Unusually resistant to discoloration. Shelf life is 12+ months. Processing: 2/1 ratio. Pot life: 40-60 minutes. Applications: Pourable tabletops and countertops, light-transmitting dielectric, analytical & other embedments.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Abatron-AboCast-8008-6AboCure-8008-6-Epoxy-nbspdiscontinued-.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	Typical value for Abatron "VR" Epoxies.
Tensile Strength, Ultimate	55.0 MPa	7980 psi	Typical value for Abatron "VR" Epoxies.
Compressive Yield Strength	62.0 MPa	8990 psi	Typical value for Abatron "VR" Epoxies.

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	75.0 °C	167 °F	70-80°C (160-175°F) Heat distortion temperature.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China