

Abatron AboCast 8101-1/AboCure 8101-1 Epoxy (discontinued **)

Category : Polymer , Thermoset , Epoxy

Material Notes:

Data provided by the manufacturer, Abatron, Inc. Medium-viscosity, Light Amber color. Shelf life is 12+ months. Corrosion Resistance Best Abatron "VR" Epoxy for heat, solvent and chemical resistance. Processing: 2/1 ratio. Pot life: 1-2 hrs. Full properties developed by heat cure or postcure. Applications: Heavy-duty applications requiring good thermal, chemical, dielectric and structural properties. Information provided by Abatron, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Abatron-AboCast-8101-1AboCure-8101-1-Epoxy-nbspdiscontinued-.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	Typical value for Abatron "VR" Epoxies.
Tensile Strength, Ultimate	55.0 MPa	7980 psi	Typical value for Abatron "VR" Epoxies.
Compressive Yield Strength	62.0 MPa	8990 psi	Typical value for Abatron "VR" Epoxies.

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 - 140 °C	266 - 284 °F	Heat distortion temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China