

Abatron AboCast 8101-8/AboCure 8101-8 Epoxy (discontinued **)

Category : Polymer , Thermoset , Epoxy

Material Notes:

Data provided by the manufacturer, Abatron, Inc. Tar filled, low-viscosity, black, plasticized resurfacing and patching compound. Shelf life is 12+ months. Processing: Pot-life: 1-2 hrs. 1/1 ratio. Applications: Runway, driveway, roof, deck, dock, and boat patching and resurfacing. Can be used on asphalt, masonry, metal, wood, and concrete.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Abatron-AboCast-8101-8AboCure-8101-8-Epoxy-nbspdiscontinued-.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	Typical value for Abatron "VR" Epoxies.
Tensile Strength, Ultimate	55.0 MPa	7980 psi	Typical value for Abatron "VR" Epoxies.
Compressive Yield Strength	62.0 MPa	8990 psi	Typical value for Abatron "VR" Epoxies.

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	75.0 °C	167 °F	70-80°C (160-175°F) Heat distortion temperature.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China