

## Abatron AboCast 8103-21 High-Performance Dielectric Epoxy

Category : Polymer , Thermoset , Epoxy , Epoxy, Cast, Unreinforced

**Material Notes:**

AboCast 8103-21 is a dielectric in/outdoor epoxy system with superior arc-track resistance, high voltage and heat resistance, low ash and ion content, and it is chlorine-free. This system combines rigidity, heat resistance, and good thermocycling properties.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-AboCast-8103-21-High-Performance-Dielectric-Epoxy.php](http://www.lookpolymers.com/polymer_Abatron-AboCast-8103-21-High-Performance-Dielectric-Epoxy.php)

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in <sup>3</sup>	Part B
	1.14 g/cc	0.0411 lb/in <sup>3</sup>	Part A

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.2 MPa	8000 psi	
Elongation at Break	27 %	27 %	
Tensile Modulus	5.45 GPa	790 ksi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	100 °C	212 °F	Deflection Temp at unknown load

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	
Dielectric Constant	2.9	2.9	
	@Frequency 60.0 Hz, Temperature 23.0 °C	@Frequency 60.0 Hz, Temperature 73.4 °F	
	3.2	3.2	
Dissipation Factor	@Frequency 60.0 Hz, Temperature 100 °C	@Frequency 60.0 Hz, Temperature 212 °F	
	3.3	3.3	
	@Frequency 60.0 Hz, Temperature 150 °C	@Frequency 60.0 Hz, Temperature 302 °F	
Dissipation Factor	0.010	0.010	
	@Frequency 60.0 Hz, Temperature 23.0 °C	@Frequency 60.0 Hz, Temperature 73.4 °F	
	0.031	0.031	

Electrical Properties	Metric @Frequency 60.0 Hz, Temperature 100 °C	English @Frequency 60.0 Hz, Temperature 212 °F	Comments
	0.080	0.080	
	@Frequency 60.0 Hz, Temperature 150 °C	@Frequency 60.0 Hz, Temperature 302 °F	
Arc Resistance	>= 150 sec	>= 150 sec	

Processing Properties	Metric	English	Comments
Cure Time	120 - 180 min	2.00 - 3.00 hour	
	@Temperature 100 °C	@Temperature 212 °F	
	60.0 - 240 min	1.00 - 4.00 hour	optional
	@Temperature 120 - 160 °C	@Temperature 248 - 320 °F	
Pot Life	30 min	30 min	
	@Temperature 80.0 °C	@Temperature 176 °F	
	>= 480 min	>= 480 min	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Arc-Track Free (min)	> 2000	2.5 KV
Color	Clear	
Parts by Weight (pbw)	100	Part A
	65	Part B
Thermal Shock Resistance	Scale 0 (poor) to 10 (excellent)	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China