

Abatron AboCast 8103-29 High-Performance Dielectric Epoxy

Category : Polymer , Thermoset , Epoxy , Epoxy, Cast, Unreinforced

Material Notes:

AboCast 8103-29 is a dielectric in/outdoor epoxy system with superior arc-track resistance, high voltage and heat resistance, low ash and ion content, and it is chlorine-free. This system has high heat conductivity, low thermal expansion, and negligible shrinkage.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Abatron-AboCast-8103-29-High-Performance-Dielectric-Epoxy.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	<= 25.0 °C	<= 77.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Constant	5.4	5.4	
	@Frequency 60.0 Hz, Temperature 100 °C	@Frequency 60.0 Hz, Temperature 212 °F	
Dissipation Factor	0.088	0.088	
	@Frequency 60.0 Hz, Temperature 100 °C	@Frequency 60.0 Hz, Temperature 212 °F	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	
	@Temperature 100 - 120 °C	@Temperature 212 - 248 °F	
	120 - 240 min	2.00 - 4.00 hour	
	@Temperature 120 - 160 °C	@Temperature 248 - 320 °F	optional
Pot Life	30 min	30 min	
	@Temperature 80.0 °C	@Temperature 176 °F	
	>= 480 min	>= 480 min	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Arc-Track Free (min)	> 2000	2.5 KV
Color	Gray or Custom	
Parts by Weight (pbw)	100	Part A
		Part B

Descriptive Properties	Value	Comments
Thermal Shock Resistance	Scale 0 (poor) to 10 (excellent)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China