

## Abatron AboCast 8103-30 High-Performance Dielectric Epoxy

Category : Polymer , Thermoset , Epoxy , Epoxy, Cast, Unreinforced

### Material Notes:

AboCast 8103-30 is a dielectric in/outdoor epoxy system with superior arc-track resistance, high voltage and heat resistance, low ash and ion content, and it is chlorine-free. This system has high heat conductivity, low thermal expansion, and negligible shrinkage.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-AboCast-8103-30-High-Performance-Dielectric-Epoxy.php](http://www.lookpolymers.com/polymer_Abatron-AboCast-8103-30-High-Performance-Dielectric-Epoxy.php)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	95.0 °C	203 °F	Deflection Temp at unknown load

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+13 ohm-cm	4.00e+13 ohm-cm	
Dielectric Constant	3.4	3.4	
	@Frequency 60.0 Hz, Temperature 23.0 °C	@Frequency 60.0 Hz, Temperature 73.4 °F	
	4.2	4.2	
	@Frequency 60.0 Hz, Temperature 100 °C	@Frequency 60.0 Hz, Temperature 212 °F	
	4.5	4.5	
	@Frequency 60.0 Hz, Temperature 150 °C	@Frequency 60.0 Hz, Temperature 302 °F	
Dielectric Strength	13.8 kV/mm	350 kV/in	S/T
Dissipation Factor	0.014	0.014	
	@Frequency 60.0 Hz, Temperature 23.0 °C	@Frequency 60.0 Hz, Temperature 73.4 °F	
	0.077	0.077	
	@Frequency 60.0 Hz, Temperature 100 °C	@Frequency 60.0 Hz, Temperature 212 °F	
	0.12	0.12	
	@Frequency 60.0 Hz, Temperature 150 °C	@Frequency 60.0 Hz, Temperature 302 °F	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	
	@Temperature 100 - 120 °C	@Temperature 212 - 248 °F	

Processing Properties	Metric 40 min	English 00 hour	Comments
	@Temperature 120 - 160 °C	@Temperature 248 - 320 °F	optional
Pot Life	30 min	30 min	
	@Temperature 80.0 °C	@Temperature 176 °F	
	>= 480 min	>= 480 min	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Arc-Track Free (min)	> 2000	2.5 KV
Color	Gray or Custom	
Parts by Weight (pbw)	100	Part A
	18.5	Part B
Thermal Shock Resistance	Scale 0 (poor) to 10 (excellent)	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China