

Abatron AboCast/AboCure 8109-2

Category : Polymer , Adhesive , Thermoset , Epoxy

Material Notes:

High melting point. Filled version. Processing: 100/10 pbw; 90 minute potlife; mix at 130-140°C (270 °F); cures in 16 h/120°C (250°F), 10 h/140°C (285°F), 8 h/160°C (320°F), 2 h/ 200°C (390°F). Applications: Heavy duty casting and potting.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Abatron-AboCastAboCure-8109-2.php

Physical Properties	Metric	English	Comments
Density	1.75 g/cc	0.0632 lb/in ³	
Water Absorption	0.25 - 0.30 %	0.25 - 0.30 %	(60x10X4 mm bar) after 10 days at 20°C (77°F)
	0.30 - 0.35 %	0.30 - 0.35 %	(60x10X4 mm bar) after 1 hour at 100°C (212°F)
Viscosity	5000 - 50000 cP	5000 - 50000 cP	
	@Temperature 120 °C	@Temperature 248 °F	
Vapor Pressure	<= 0.0000133 bar	<= 0.0100 torr	AboCure
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	<= 0.00133 bar	<= 1.00 torr	AboCast
	@Temperature 180 °C	@Temperature 356 °F	
	0.00133 bar	1.00 torr	AboCure
	@Temperature 100 °C	@Temperature 212 °F	
	0.00373 bar	2.80 torr	AboCure
	@Temperature 120 °C	@Temperature 248 °F	
	0.0133 bar	10.0 torr	AboCure
	@Temperature 135 °C	@Temperature 275 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	62.05 MPa	9000 psi	
Flexural Yield Strength	131 MPa	19000 psi	
Compressive Yield Strength	193.1 MPa	28010 psi	

Thermal Properties	Metric	English	Comments
	30.0 - 35.0 µm/m-°C	16.7 - 19.4 µin/in-°F	

CTE linear Thermal Properties	Metric @ Temperature 20.0 °C	English @ Temperature 68.0 °F	Comments
Thermal Conductivity	0.590 - 0.670 W/m-K	4.09 - 4.65 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	115 °C	239 °F	Deflection temperature; load unknown

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.50e+16 ohm-cm	>= 1.50e+16 ohm-cm	
Dielectric Constant	3.7 - 4.0	3.7 - 4.0	
	@Frequency 50 Hz	@Frequency 50 Hz	
	3.9 - 4.2	3.9 - 4.2	
Dielectric Strength	@Frequency 1000 Hz	@Frequency 1000 Hz	
	4.0 - 4.2	4.0 - 4.2	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	17.72 - 20.67 kV/mm	450.1 - 525.0 kV/in	Short time value
	@Thickness 3.17 mm	@Thickness 0.125 in	
Dissipation Factor	0.0090 - 0.014	0.0090 - 0.014	
	@Frequency 50 Hz	@Frequency 50 Hz	
	0.0090 - 0.015	0.0090 - 0.015	
Dissipation Factor	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.015 - 0.025	0.015 - 0.025	
Dissipation Factor	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Processing Properties	Metric	English	Comments
Processing Temperature	130 - 140 °C	266 - 284 °F	
Pot Life	90.0 min	90.0 min	
	@Temperature 120 °C	@Temperature 248 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China