

## Abatron AboCast/AboCure 8508-1/8508-1 Primerless, High-Solids Epoxy (discontinued \*\*)

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

### Material Notes:

Primerless, high-solids epoxy structural paint for concrete, wood, metal and composite surfaces. 2-component system in standard and custom colors. Suggested Uses: Protective and decorative painting of floors and most rigid surfaces in industrial, construction, marine and general environment. Primer and color base for polyurethanes and other paints. Protection against water, salt, weathering, fuels, oils, alkalis, detergents, diluted acids. Renewing or skid-proofing concrete, metal and wood floors. Outstanding for wear resistance, hardness, flexibility, versatility, permanence. Can be applied with spray, brush, or roller. Processing: Ratio by volume: 1/1 Cure Schedule: Room temperature cure 6-8 hours for handling, 2-3 days for full physical properties, and 6-7 days for full resistance properties. Optional high temperature bake 35-45 minutes at 150°F, 20-30 minutes at 200°F, or 15-20 minutes at 250°F. Baking is useful for fast optimum results. Information provided by Abatron.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-AboCastAboCure-8508-18508-1-Primerless-High-Solids-Epoxy-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Abatron-AboCastAboCure-8508-18508-1-Primerless-High-Solids-Epoxy-nbspdiscontinued-.php)

| Physical Properties   | Metric    | English                   | Comments |
|-----------------------|-----------|---------------------------|----------|
| Density               | 1.26 g/cc | 0.0455 lb/in <sup>3</sup> |          |
| Solids Content        | 64 - 65 % | 64 - 65 %                 |          |
| Viscosity Measurement | 73        | 73                        | K.U.     |

| Processing Properties | Metric        | English       | Comments |
|-----------------------|---------------|---------------|----------|
| Pot Life              | 480 - 720 min | 480 - 720 min |          |

| Descriptive Properties | Value | Comments  |
|------------------------|-------|-----------|
| Pencil Hardness        | 3     | Overnight |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China