

## Abatron AboWeld 48-8/AboCure 48-8 Adhesive/Casting Resin

Category : Polymer , Adhesive , Thermoset

### Material Notes:

Information provided by Abatron, Inc. Adheres to metal, glass, ceramics, wood, masonry, etc. Material properties are based on a 2/1 mix ratio. Resin is white, curing agent is black. Gray blend allows for visual inspection of proper mixing and ratios. Shelf life: 12+ months (unmixed). Processing: 100/(40-100) ratio. Pot life: 100 g, 30-40 min. at 25°C (77°F). Hardens in 3-5 hours at 25°C (77°F), 4-6 min. at 80°C (175°F), 2 min. at 120°C (250°F), 24 sec to 1 min. at 150°C (300°F). Corrosion Resistance: good resistance to atmospheric conditions, soft and salt water, alkalis and diluted acids.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-AboWeld-48-8AboCure-48-8-AdhesiveCasting-Resin.php](http://www.lookpolymers.com/polymer_Abatron-AboWeld-48-8AboCure-48-8-AdhesiveCasting-Resin.php)

Physical Properties	Metric	English	Comments
Water Absorption	0.20 %	0.20 %	after 24 hrs.
Viscosity Measurement	200 @Temperature 25.0 - 27.0 °C	200 @Temperature 77.0 - 80.6 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	100/40 pbw; 68 at 100/80 pbw; 66 (60 after 10 sec) at 100/100 pbw
Tensile Strength, Ultimate	51.0 MPa	7400 psi	Typical averaged test results for Abatron Adhesive/Casting Resins.
Elongation at Break	3.0 %	3.0 %	Typical averaged test results for Abatron Adhesive/Casting Resins.
Flexural Yield Strength	83.0 MPa	12000 psi	Typical averaged test results for Abatron Adhesive/Casting Resins.
Compressive Yield Strength	115 MPa	16700 psi	Typical averaged test results for Abatron Adhesive/Casting Resins.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China