

## Abatron AboWeld 8708-8 One-Component Structural/Dielectric Epoxy

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy, Cast, Unreinforced , Epoxy, Thermally Conductive

### Material Notes:

AboWeld 8708-8 is a highly filled, class H (180°C) structural, heat-conductive adhesive paste for FAST high-temperature curing. Suggested Uses: Structural bonding; Casting; Potting; Encapsulating; Embedding applications where 2-component systems are not practical; Appliances; Radiators; Electronic components; Medical equipment; Excellent bond to metals, ceramics, glass; Assembly; Patching; Filling; Resurfacing; Insulation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-AboWeld-8708-8-One-Component-StructuralDielectric-Epoxy.php](http://www.lookpolymers.com/polymer_Abatron-AboWeld-8708-8-One-Component-StructuralDielectric-Epoxy.php)

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0649 lb/in <sup>3</sup>	
Viscosity	1500 cP	1500 cP	
	@Temperature 100 °C	@Temperature 212 °F	
	180000 cP	180000 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	>= 70	>= 70	
	@Temperature 120 °C	@Temperature 248 °F	
	90	90	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	33.0 µm/m-°C	18.3 µin/in-°F	
	@Temperature -50.0 - 50.0 °C	@Temperature -58.0 - 122 °F	
Thermal Conductivity	0.761 W/m-K	5.28 BTU-in/hr-ft <sup>2</sup> -°F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	20.0 min	0.333 hour	
	@Temperature 180 °C	@Temperature 356 °F	

Processing Properties	Metric <sup>in</sup>	English <sup>our</sup>	Comments
	@Temperature 150 °C	@Temperature 302 °F	
	120 - 180 min	2.00 - 3.00 hour	
	@Temperature 121 °C	@Temperature 250 °F	
Shelf Life	<= 5.00 Month	<= 5.00 Month	

Descriptive Properties	Value	Comments
Color	Black	
Hardening Time (min)	12	150°C
	4	180°C
	60	121°C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China