

## Abatron MasterMold 12-8 Flexible Mold Making Compound

Category : Polymer , Thermoset , Polyurethane, TS

### Material Notes:

Master mold 12-8 is a pourable version of MasterMold 12-3 for creating a mold by pouring it into, or around, the model. Processing: Part A Resin: Clear, pourable viscous liquid, 8.7 lbs/gal Part B Converter: Pink, pourable viscous liquid, 8.9 lbs/gal Information provided by Abatron.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Abatron-MasterMold-12-8-Flexible-Mold-Making-Compound.php](http://www.lookpolymers.com/polymer_Abatron-MasterMold-12-8-Flexible-Mold-Making-Compound.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	28	28	
Tensile Strength at Break	0.393 MPa	57.0 psi	
Elongation at Break	600 %	600 %	

Processing Properties	Metric	English	Comments
Dry Time	12 - 16 hour	12 - 16 hour	Hard
Pot Life	60 - 90 min	60 - 90 min	Working life

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China