

Aclo Accucomp ABS ABS810L Medium Impact Grade

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Impact Grade, Molded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accucomp-ABS-ABS810L-Medium-Impact-Grade.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	MD; ASTM D955
Melt Flow	2.8 g/10 min	2.8 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	42.0 MPa	6090 psi	ASTM D638
Elongation at Break	26 %	26 %	ASTM D638
Tensile Modulus	1.650 GPa	239.3 ksi	ASTM D638
Flexural Strength	65.0 MPa	9430 psi	ASTM D790
Flexural Modulus	2.60 GPa	377 ksi	ASTM D790
Izod Impact, Notched	2.67 J/cm	5.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	87.2 °C	189 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China