

Aclo Accucomp ABS ABS892DL High Heat Grade

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accucomp-ABS-ABS892DL-High-Heat-Grade.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	MD; ASTM D955
Melt Flow	0.30 g/10 min	0.30 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ASTM D785
Tensile Strength at Break	45.0 MPa	6530 psi	ASTM D638
Tensile Strength, Yield	54.0 MPa	7830 psi	ASTM D638
Elongation at Break	12 %	12 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	1.80 GPa	261 ksi	ASTM D638
Flexural Strength	75.98 MPa	11020 psi	ASTM D790
Flexural Modulus	2.699 GPa	391.5 ksi	ASTM D790
Izod Impact, Notched	1.76 J/cm	3.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	87.8 °C	190 °F	
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0625 in	UL File #E56070

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China