

Aclo Accutech ABS ABS833G30L Glass Reinforced

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 30% Glass Fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-ABS-ABS833G30L-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	0.90 g/10 min	0.90 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	107	107	ASTM D785
Tensile Strength at Break	89.98 MPa	13050 psi	ASTM D638
Tensile Strength, Yield	89.98 MPa	13050 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	5.199 GPa	754.1 ksi	ASTM D638
Flexural Strength	126.0 MPa	18270 psi	ASTM D790
Flexural Modulus	8.1986 GPa	1189.1 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	102 °C	216 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China