

Aclo Accutech ABS ABS833G40L Glass Reinforced

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 40% Glass Fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-ABS-ABS833G40L-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	0.80 g/10 min	0.80 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	103	103	ASTM D785
Tensile Strength at Break	93.98 MPa	13630 psi	ASTM D638
Tensile Strength, Yield	93.98 MPa	13630 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Tensile Modulus	6.099 GPa	884.6 ksi	ASTM D638
Flexural Strength	131 MPa	19000 psi	ASTM D790
Flexural Modulus	10.398 GPa	1508.1 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	102 °C	216 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	97.2 °C	207 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China