

## Aclo Accutech Polycarbonate POL050G10L Glass Reinforced

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 10% Glass Filled

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polycarbonate-POL050G10L-Glass-Reinforced.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polycarbonate-POL050G10L-Glass-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	MD; ASTM D955
Melt Flow	16 g/10 min	16 g/10 min	ASTM D1238
Ash	10 %	10 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength at Break	66.0 MPa	9570 psi	ASTM D638
Tensile Strength, Yield	75.01 MPa	10880 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	2.80 GPa	406 ksi	ASTM D638
Flexural Strength	123.0 MPa	17840 psi	ASTM D790
Flexural Modulus	3.800 GPa	551.1 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	142 °C	288 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	134 °C	273 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China