

Aclo Accutech Polypropylene Copolymer CP0436G25M5CL Glass/Mineral Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0436G25M5CL-GlassMineral-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	75	75	ASTM D785
Tensile Strength at Break	45.0 MPa	6530 psi	ASTM D638
Tensile Strength, Yield	46.0 MPa	6670 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	3.40 GPa	493 ksi	ASTM D638
Flexural Strength	68.0 MPa	9860 psi	ASTM D790
Flexural Modulus	3.900 GPa	565.6 ksi	ASTM D790
Izod Impact, Notched	1.44 J/cm	2.70 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	155 °C	311 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	129 °C	264 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China