

## Aclo Accutech Polypropylene Copolymer CP0436T20L1 Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polypropylene-Copolymer-CP0436T20L1-Talc-Reinforced.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0436T20L1-Talc-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	MD; ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
Ash	20 %	20 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	60	60	ASTM D785
Tensile Strength at Break	18.0 MPa	2610 psi	ASTM D638
Tensile Strength, Yield	23.0 MPa	3340 psi	ASTM D638
Elongation at Break	20 %	20 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	1.80 GPa	261 ksi	ASTM D638
Flexural Strength	31.0 MPa	4500 psi	ASTM D790
Flexural Modulus	1.80 GPa	261 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm	1.40 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 °C	230 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	57.8 °C	136 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China