

## Aclo Accutech Polypropylene Copolymer CP0436T40L Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polypropylene-Copolymer-CP0436T40L-Talc-Reinforced.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0436T40L-Talc-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	MD; ASTM D955
Melt Flow	11 g/10 min	11 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	51	51	ASTM D785
Tensile Strength at Break	17.0 MPa	2470 psi	ASTM D638
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D638
Elongation at Break	15 %	15 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	2.299 GPa	333.5 ksi	ASTM D638
Flexural Strength	29.0 MPa	4210 psi	ASTM D790
Flexural Modulus	2.499 GPa	362.5 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	114 °C	237 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	61.1 °C	142 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China