

## Aclo Accutech Polypropylene Copolymer CP0436W40L Wollastonite Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polypropylene-Copolymer-CP0436W40L-Wollastonite-Reinforced.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0436W40L-Wollastonite-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	MD; ASTM D955
Melt Flow	11 g/10 min	11 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	50	50	ASTM D785
Tensile Strength at Break	17.0 MPa	2470 psi	ASTM D638
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D638
Elongation at Break	18 %	18 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	2.699 GPa	391.5 ksi	ASTM D638
Flexural Strength	26.0 MPa	3770 psi	ASTM D790
Flexural Modulus	2.699 GPa	391.5 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	113 °C	235 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	66.1 °C	151 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China