

Aclo Accutech Polypropylene Copolymer CP0437G20M10CL Glass/Mineral Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0437G20M10CL-GlassMineral-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	69	69	ASTM D785
Tensile Strength at Break	35.0 MPa	5080 psi	ASTM D638
Tensile Strength, Yield	37.0 MPa	5370 psi	ASTM D638
Elongation at Break	9.0 %	9.0 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	2.899 GPa	420.5 ksi	ASTM D638
Flexural Strength	52.0 MPa	7540 psi	ASTM D790
Flexural Modulus	3.20 GPa	464 ksi	ASTM D790
Izod Impact, Notched	1.55 J/cm	2.90 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	152 °C	306 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China