

Aclo Accutech Polypropylene Copolymer CP0437G25M5CL Glass/Mineral Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0437G25M5CL-GlassMineral-Reinforced-Coupled.php

| Physical Properties | Metric | English | Comments |
|-----------------------|--------------|---------------------------|---------------|
| Density | 1.10 g/cc | 0.0397 lb/in ³ | ASTM D792 |
| Linear Mold Shrinkage | 0.0010 cm/cm | 0.0010 in/in | MD; ASTM D955 |
| Melt Flow | 9.0 g/10 min | 9.0 g/10 min | ASTM D1238 |
| Ash | 30 % | 30 % | ASTM D2584 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-----------|---------------|-----------|
| Hardness, Rockwell R | 75 | 75 | ASTM D785 |
| Tensile Strength at Break | 40.0 MPa | 5800 psi | ASTM D638 |
| Tensile Strength, Yield | 42.0 MPa | 6090 psi | ASTM D638 |
| Elongation at Break | 9.0 % | 9.0 % | ASTM D638 |
| Elongation at Yield | 5.0 % | 5.0 % | ASTM D638 |
| Tensile Modulus | 3.20 GPa | 464 ksi | ASTM D638 |
| Flexural Strength | 60.0 MPa | 8700 psi | ASTM D790 |
| Flexural Modulus | 3.499 GPa | 507.5 ksi | ASTM D790 |
| Izod Impact, Notched | 1.66 J/cm | 3.10 ft-lb/in | ASTM D256 |

| Thermal Properties | Metric | English | Comments |
|---|--------|---------|-----------|
| Deflection Temperature at 0.46 MPa (66 psi) | 153 °C | 307 °F | ASTM D648 |
| Deflection Temperature at 1.8 MPa (264 psi) | 126 °C | 259 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China