

Aclo Accutech Polypropylene Copolymer CP0437T30L Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0437T30L-Talc-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	MD; ASTM D955
Melt Flow	16 g/10 min	16 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	50	50	ASTM D785
Tensile Strength at Break	13.0 MPa	1890 psi	ASTM D638
Tensile Strength, Yield	16.0 MPa	2320 psi	ASTM D638
Elongation at Break	15 %	15 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	1.500 GPa	217.5 ksi	ASTM D638
Flexural Strength	20.0 MPa	2900 psi	ASTM D790
Flexural Modulus	1.900 GPa	275.5 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	92.2 °C	198 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	53.9 °C	129 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China