

Aclo Accutech Polypropylene Homopolymer HP0334T30L1 Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0334T30L1-Talc-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	MD; ASTM D955
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Ash	29.2 %	29.2 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	84	84	ASTM D785
Tensile Strength at Break	30.0 MPa	4350 psi	ASTM D638
Tensile Strength, Yield	35.0 MPa	5080 psi	ASTM D638
Elongation at Break	12 %	12 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	2.20 GPa	319 ksi	ASTM D638
Flexural Strength	47.0 MPa	6820 psi	ASTM D790
Flexural Modulus	3.60 GPa	522 ksi	ASTM D790
Izod Impact, Notched	0.352 J/cm	0.660 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China