

## Aclo Accutech Polypropylene Homopolymer HP0336C40L Calcium Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Calcium Carbonate (CaCO3) Filler

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polypropylene-Homopolymer-HP0336C40L-Calcium-Reinforced.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336C40L-Calcium-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.205 g/cc	0.04353 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	MD; ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	86	86	ASTM D785
Tensile Strength at Break	17.0 MPa	2470 psi	ASTM D638
Tensile Strength, Yield	26.0 MPa	3770 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	2.40 GPa	348 ksi	ASTM D638
Flexural Strength	35.0 MPa	5080 psi	ASTM D790
Flexural Modulus	2.200 GPa	319.1 ksi	ASTM D790
Izod Impact, Notched	0.400 J/cm	0.750 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 °C	230 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	62.2 °C	144 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China