

Aclo Accutech Polypropylene Homopolymer HP0336G10CL Glass Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Glass Fiber Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336G10CL-Glass-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	MD; ASTM D955
Melt Flow	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Ash	10 %	10 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	101	101	ASTM D785
Tensile Strength at Break	33.0 MPa	4790 psi	ASTM D638
Tensile Strength, Yield	37.0 MPa	5370 psi	ASTM D638
Elongation at Break	9.0 %	9.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	2.20 GPa	319 ksi	ASTM D638
Flexural Strength	53.0 MPa	7690 psi	ASTM D790
Flexural Modulus	2.299 GPa	333.5 ksi	ASTM D790
Izod Impact, Notched	0.278 J/cm	0.520 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China