

Aclo Accutech Polypropylene Homopolymer HP0336G20M10CL Glass/Mineral Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336G20M10CL-GlassMineral-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	MD; ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	92	92	ASTM D785
Tensile Strength at Break	56.0 MPa	8120 psi	ASTM D638
Tensile Strength, Yield	57.0 MPa	8270 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	3.699 GPa	536.5 ksi	ASTM D638
Flexural Strength	85.98 MPa	12470 psi	ASTM D790
Flexural Modulus	4.799 GPa	696.1 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	154 °C	309 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	133 °C	271 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China