

## Aclo Accutech Polypropylene Homopolymer HP0336G40CL Glass Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Glass Fiber Filler

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Aclo-Accutech-Polypropylene-Homopolymer-HP0336G40CL-Glass-Reinforced-Coupled.php](http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336G40CL-Glass-Reinforced-Coupled.php)

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength at Break	81.98 MPa	11890 psi	ASTM D638
Tensile Strength, Yield	81.98 MPa	11890 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	4.599 GPa	667.1 ksi	ASTM D638
Flexural Strength	117.0 MPa	16970 psi	ASTM D790
Flexural Modulus	7.2988 GPa	1058.6 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	145 °C	293 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	160 °C	320 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**