

Aclo Accutech Polypropylene Homopolymer HP0336T10L1 Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336T10L1-Talc-Reinforced.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	MD; ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
Ash	10 %	10 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	99	99	ASTM D785
Tensile Strength at Break	23.0 MPa	3340 psi	ASTM D638
Tensile Strength, Yield	37.0 MPa	5370 psi	ASTM D638
Elongation at Break	22 %	22 %	ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Tensile Modulus	1.40 GPa	203 ksi	ASTM D638
Flexural Strength	49.0 MPa	7110 psi	ASTM D790
Flexural Modulus	2.099 GPa	304.5 ksi	ASTM D790
Izod Impact, Notched	0.299 J/cm	0.560 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	118 °C	244 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China