

Aclo Accutech Polypropylene Homopolymer HP0339G30CL Glass Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0339G30CL-Glass-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength at Break	69.98 MPa	10150 psi	ASTM D638
Tensile Strength, Yield	71.98 MPa	10440 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	4.000 GPa	580.1 ksi	ASTM D638
Flexural Strength	89.98 MPa	13050 psi	ASTM D790
Flexural Modulus	5.599 GPa	812.1 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	156 °C	313 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	143 °C	289 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China